

(10) Patent No.: US 6,306,358 B1
(45) Date of Patent: Oct. 23, 2001

B-7-53610 6/1995 (JP).
A-7-172806 7/1995 (JP).

OTHER PUBLICATIONS

S. Kurita et al., "Pressureless Sintering of h-BN for Continuous Temperature Measurement of Melts" Shigen-Sozai-Gakkai-Shi(=J. Resources and Materials Assoc.) vol. 2 (1989) pp. 201-204.

J. Thomas, Jr., et al., "Turbostratic¹. Boron Nitride, Thermal Transformation to Ordered-layer-lattice Boron Nitride" *Journal of the American Chemical Society*, vol. 84 (1963) pp. 4619-4622.

* cited by examiner

Primary Examiner—Wayne Langel

(74) Attorney, Agent, or Firm—Morrison & Foerster LLP

(57) ABSTRACT

Turbostratic boron nitride (t-BN) powder having excellent sinterability. A mixture of boric acid anhydride and urea is charged in a reaction vessel together with alkali-borate, heated step by step in the vessel in a nonoxidizing gas atmosphere of one atmospheric pressure or above, and kept at a temperature from 850° C. to 950° C. to yield an intermediate product formal substantially of an amorphous boron nitride powder (first reaction step). Then the intermediate product is heated and kept at a temperature from 1200° C. to 1400° C. to crystallize crystalline t-BN, and the product is purified by washing with water and aqueous solution to obtain pure crystalline t-BN powder.

6 Claims, 8 Drawing Sheets